

Technical Data

BALTOFLAKE S2000



Product description

Baltoflake S2000 is a quick curing, high build, abrasion resistant, glass flake reinforced polyester coating that gives long time corrosion protection.

Recommended use

Steel structures in general and items subject to extreme mechanical wear in particular. May also be used for protection of aluminium and concrete (special designed systems).

Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (μm)	500	1000	750
Film thickness, wet (μm)	520	1040	780
Theoretical spreading rate (m^2/l)	1,9	0,9	1,3

Physical properties

Colour Limited number
Solids (vol %)* 96 ± 2

Flash point $34^\circ\text{C} \pm 2$ (Setaflash)

Gloss Semiflat
Gloss retention Very good
Water resistance Excellent
Abrasion resistance Excellent
Solvent resistance Very good
Chemical resistance Very good
Flexibility Limited

Compatibility with cathodic protection Very good

*Measured according to ISO 3233:1998 (E)

The solid content may vary dependent on the temperature, ventilation/wind during the application and film thickness.

Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

Bare steel

Blast cleaning to Sa 2½. (ISO 8501-1:1988). Roughness: using abrasives suitable to achieve a coarse surface of Grade Medium G (50-85 μm , Ry5) (ISO 8503-2).

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying. The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

Application methods

Spray	Use normal airless spray or two-comp. airless spray equipment
Brush	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.
Roller	May be used for small areas but not recommended for first primer coat, however when using roller application care must be taken to apply sufficient material in order to achieve the specified dry film thickness.

Application data

Mixing ratio (volume)	See separate table.
Pot life (23°C)	45 - 55 minutes (Reduced at higher temp.)
Thinner	If needed max. 5% styrene.
Cleaner	Acetone, Jotun Thinner No. 17 or Jotun Thinner No. 27
Guiding data airless spray	
Pressure at nozzle	15 - 25 MPa (150-250 kp/cm ² , 2100-4000 psi.).
Ratio/Capacity:	>45:1, min. 12 l per minute. Slow moving piston.
Nozzle tip	0.69 - 1.97 mm (0.027 - 0.038").
Spray angle	40 - 80°
Filter	To be removed
Note	For further details please see separate "Working Manual".

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Substrate temperature	10°C	23°C	40°C
Surface dry	3 h	2 h	2 h
Through dry	5 h	2 h	2 h
Cured	4 d	2 d	1 d
Dry to recoat, minimum	5 h	2 h	2 h
Dry to recoat, maximum ¹	10 h	6 h	6 h

1. The surface should be dry and free from any contamination prior to application. If the maximum dry to recoat time is exceeded, please contact Jotun for advice.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Over Sa 2½:

Baltoflake S2000 1-2 x 750 µm (Dry Film Thickness)

Other systems may be specified, depending on area of use

Mixing Ratio Table:

Choose curing agent and, if necessary, inhibitor or accelerator according to the table below. Inhibitor or accelerator (if used) must be thoroughly mixed with Baltoflake S2000 before adding the required amount of Norpol peroxide. Mechanical agitation for one minute or more.

Temperature	Addition	Notes
10-15°C	Norpol accelerator 9802P/S: 2 vol% (320 ml to 16 l) Norpol peroxide No 1: 2 vol% (320 ml to 16 l)	Temperature applies to the temperature of the steel. Paint temperature: 15-20°C.
15-20°C	Norpol peroxide No 1: 2 vol% (320 ml to 16 l)	
20-25°C	Norpol peroxide No 1: 1.25 vol% (200 ml to 16 l)	Temperature of steel and paint.
25-35°C	Norpol inhibitor 9851: 1.25 vol% (200 ml to 16 l) Norpol peroxide No 1: 1.25 vol% (200 ml to 16 l)	Temperature applies to the temperature of the paint. Steel temperature above 25°C.
35-40°C	Norpol inhibitor 9851: 2,5 vol % (400 ml to 16 l) Norpol peroxide No 1: 1.25 vol% (200 ml to 16 l)	

Note: Check temperature of pump during application. Friction in piston may cause increase in temperature. If this should happen, keep pump going to get heated Baltoflake S2000 out as quick as possible.

If the temperature is ranging near the max. temperature in a zone, it is recommended to reduce the content of peroxide/accelerator respectively, or to increase the content of inhibitor.

Approved alternatives to Norpol Peroxide No 1 can be used. Please contact your local Jotun office.

Warning: Accelerator and MEK-peroxide must never be mixed directly together.

Storage

The product must be stored below 25°C and in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

SHELF LIFE: 6 months, at 23°C, subject to re-inspection thereafter. Shelf life very much depends on temperature. Lower temperatures (if possible below freezing point) will lengthen the shelf life considerably, while high temperature may lead to gelling in the tin.

Handling

Handle Norpol Peroxide with care. Avoid that it comes in contact with combustible materials. Accelerator and peroxide must never be mixed directly together.

Packing size

20 litre unit: 16 litres in a 20 litre container

Packing may vary from country to country according to local requirements.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Footer - English

Head Office & Nordic	Europe	Middle East	South East Asia
Jotun A/S	Jotun Paints (Europe) Ltd.	Jotun U.A.E Ltd. LLC.	Jotun (Singapore) Pte. Ltd.
P.O. Box 2021	Stather Road, Flixborough		No 11-15, Sixth Lok Yang
N-3248 Sandefjord	North Lincolnshire DN15	Al Quoz Industrial Area	Road
Norway	8RR	P.O Box 3671	Jurong
Phone +47 33 45 70 00	United Kingdom	Dubai U.A.E	Singapore 628 111
Fax +47 33 46 46 13	Phone +44 172 44 00 000	Phone +971 4 3 39 50 00	Phone +65 6265 4711
	Fax +44 172 44 00 100	Fax +971 4 3 38 06 66	Fax +65 6265 7484

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 28 FEBRUARY 2005 BY JOTUN
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED