

# Technical Data

## TANKGUARD STORAGE



### Product description

Tankguard Storage is a two-component, high solid phenolic epoxy coating with high resistance to a wide range of chemicals and solvents.

---

### Recommended use

Corrosion protection for the internal lining of steel storage tanks being resistant to a wide range of chemicals including, but not limited to, crude oil and aromatic and aliphatic solvents and others.

---

### Film thickness and spreading rate

|  | Minimum | Maximum | Typical |
|--|---------|---------|---------|
| Film thickness, dry ( $\mu\text{m}$ )                | 100     | 200     | 125     |
| Film thickness, wet ( $\mu\text{m}$ )                | 160     | 320     | 200     |
| Theoretical spreading rate ( $\text{m}^2/\text{l}$ ) | 6,3     | 3,2     | 5       |

---

### Physical properties

|                     |  |
|---------------------|--|
| Colour              | Light Red, Red   |
| Solids (vol %)*     | 63 $\pm$ 2   |
| Flash point         | 28°C $\pm$ 2 (Setaflash)   |
| VOC                 | 2,5 lbs/gal (300 gms/ltr) USA-EPA Method 24<br>310 gms/ltr UK-PG6/23(97). Appendix 3 |
| Gloss               | Flat   |
| Water resistance    | Very good  |
| Solvent resistance  | Excellent  |
| Chemical resistance | Excellent  |
| Flexibility         | Fair   |

\*Measured according to ISO 3233:1998 (E)

---

### Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

#### Bare steel

Cleanliness: Blast cleaning to min. Sa 2 ½ (ISO 8501 1:1988). Roughness: using abrasives suitable to achieve Grade Medium G (50 - 85  $\mu\text{m}$ , Ry5) (ISO 8503-2).

#### Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

---

## Condition during application

The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is required in confined areas to ensure proper drying. The coating should not be exposed to oil, chemicals or mechanical stress until cured.

---

## Application methods

Spray Use airless spray  
Brush Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.

---

## Application data

Mixing ratio (volume) 6,5:1

Mixing 6,5 parts Comp. A (base) to be mixed thoroughly with 1 part Comp. B (curing agent)

Induction time 20 minutes.

Pot life (23°C) 4 hours (Reduced at higher temp.)

Thinner/Cleaner Jotun Thinner No. 23

Guiding data airless spray

Pressure at nozzle 15 MPa (150 kp/cm<sup>2</sup>, 2100 psi)

Nozzle tip 0.46-0.69 mm (0.018-0.027")

Spray angle 40-80°

Filter Check to ensure that filters are clean.

---

## Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- \* Good ventilation (Outdoor exposure or free circulation of air)
- \* Typical film thickness
- \* One coat on top of inert substrate

| Substrate temperature               | 10°C | 15°C | 23°C | 40°C |
|-------------------------------------|------|------|------|------|
| Surface dry                         | 15 h | 12 h | 4 h  | 2 h  |
| Through dry                         | 24 h | 20 h | 10 h | 4 h  |
| Cured                               | - d  | 14 d | 7 d  | 3 d  |
| Dry to recoat, minimum <sup>2</sup> | 24 h | 20 h | 10 h | 4 h  |
| Dry to recoat, maximum <sup>1</sup> | 30 d | 30 d | 30 d | 30 d |

1. The surface should be free from chalking and contamination prior to application. If the maximum dry to recoat time is exceeded, please contact Jotun for advice.
2. In order to achieve full product resistance, a combined total of 14 days curing at minimum 15°C is required during build period.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

---

## Typical paint system

Tankguard Storage                      2 x 125 µm                      (Dry Film Thickness)

Other systems may be specified, depending on area of use

---

## Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

---

## Handling

Handle with care. Stir well before use.

---

## Packing size

20 litre unit: 16.3 litres Comp. A (base) in a 20 litre container and 2.5 litres Comp. B (curing agent) in a 3 litre container

---

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

---

## DISCLAIMER

*The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.*

| Head Office & Nordic  | Europe                     | Middle East             | South East Asia             |
|-----------------------|----------------------------|-------------------------|-----------------------------|
| Jotun A/S             | Jotun Paints (Europe) Ltd. | Jotun U.A.E Ltd. LLC.   | Jotun (Singapore) Pte. Ltd. |
| P.O. Box 2021         | Stather Road, Flixborough  |                         | No 11-15, Sixth Lok Yang    |
| N-3248 Sandefjord     | North Lincolnshire DN15    | Al Quoz Industrial Area | Road                        |
| Norway                | 8RR                        | P.O Box 3671            | Jurong                      |
| Phone +47 33 45 70 00 | United Kingdom             | Dubai U.A.E             | Singapore 628 111           |
| Fax +47 33 46 46 13   | Phone +44 172 44 00 000    | Phone +971 4 3 39 50 00 | Phone +65 6265 4711         |
|                       | Fax +44 172 44 00 100      | Fax +971 4 3 38 06 66   | Fax +65 6265 7484           |

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at [www.jotun.com](http://www.jotun.com)

ISSUED 10 NOVEMBER 2006 BY JOTUN  
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED

